

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the application:

LISTING OF CLAIMS:

1. (original): A thermoplastic polyester resin composition comprising (B) 0.1 to 50 parts by weight of a viscosity modifier for a thermoplastic polyester resin comprising
(a) 3 to 95 % by weight of alkyl (meth)acrylate containing an epoxy group,
(b) 5 to 97 % by weight of another alkyl (meth)acrylate and
(c) 0 to 92 % by weight of another vinyl monomer copolymerizable therewith, and having weight average molecular weight of 1,000 to 400,000; and (C) 1 to 50 parts by weight of a core-shell graft polymer,
based on (A) 100 parts by weight of thermoplastic polyester resin.

2. (original): The thermoplastic polyester resin composition of Claim 1, wherein said viscosity modifier for thermoplastic polyester resin (B) is a viscosity modifier for thermoplastic polyester resin comprising
(a) 15 to 95 % by weight of alkyl (meth)acrylate containing an epoxy group,
(b) 5 to 85 % by weight of another alkyl (meth)acrylate and
(c) 0 to 80 % by weight of another vinyl monomer copolymerizable therewith, and having weight average molecular weight of 1,000 to 400,000.

3. (currently amended): The thermoplastic polyester resin composition of Claim 1 or 2, wherein said core-shell graft polymer (C) is a core-shell graft polymer having as the core layer, 50 to 95 parts by weight of a rubbery polymer (d') which comprises a monomer mixture (d) containing
(d-1) 35 to 100 % by weight of a butadiene and/or alkyl acrylate monomer,
(d-2) 0 to 65 % by weight of an aromatic vinyl monomer,

Preliminary Amendment
Based on PCT/JP03/14129

(d-3) 0 to 20 % by weight of a vinyl monomer copolymerizable therewith, and

(d-4) 0 to 5 % by weight of a multi-functional monomer, and

has glass transition temperature of at most 0°C;

and as the shell layer, 5 to 50 parts by weight of a polymer (e') which comprises a monomer mixture (e) containing

(e-1) 10 to 100 % by weight of an alkyl methacrylate monomer,

(e-2) 0 to 60 % by weight of an alkyl acrylate monomer,

(e-3) 0 to 90 % by weight of an aromatic vinyl monomer,

(e-4) 0 to 25 % by weight of a cyanized vinyl monomer, and

(e-5) 0 to 20 % by weight of a vinyl monomer copolymerizable therewith.

4. (currently amended): A molded article comprising the thermoplastic polyester resin composition of Claim 1,~~2 or 3~~.

5. (currently amended): A molded article obtained by extrusion molding the thermoplastic polyester resin composition of Claim 1,~~2 or 3~~.